

Merrex Gold Inc. - Jubilee Property
Assay Results Summary: MJ-06-01 to MJ-07-18

Hole	From (m)	To (m)	Interval (m)	Weighted Average		
				Zn %	Pb %	Pb% + Zn%
MJ-06-01	209.00	209.47	0.47	1.08	1.17	2.24
MJ-06-01	228.43	237.57	9.14	1.89	0.27	2.16
including	228.43	231.40	2.97	3.51	0.18	3.69
including	228.43	229.03	0.60	9.41	0.04	9.45
including	236.12	237.57	1.45	1.96	0.93	2.89
MJ-06-02	240.03	243.38	3.35	0.81	0.28	1.09
including	240.03	240.63	0.60	1.76	1.47	3.23
MJ-06-03	365.20	371.35	6.15	0.52	0.07	0.59
including	365.20	365.80	0.60	1.04	0.04	1.08
MJ-06-05	415.15	420.00	4.85	3.52	0.45	3.97
including	415.85	416.49	0.64	23.90	2.91	26.81
MJ-06-05	426.55	427.05	0.50	2.04	0.35	2.39
MJ-06-07	392.10	394.00	1.90	1.06	0.04	1.10
MJ-06-07	396.25	410.60	14.35	0.71	0.56	1.28
including	396.25	399.65	3.40	2.12	2.11	4.23
including	399.05	399.65	0.60	5.35	0.28	5.63
MJ-06-08	414.00	416.82	2.82	2.30	1.20	3.50
including	414.00	415.25	1.25	4.17	2.57	6.74
MJ-06-10	223.30	227.30	4.00	3.34	1.32	4.66
including	224.17	225.05	0.88	13.09	5.93	19.01
MJ-06-12	218.15	222.22	4.07	4.53	0.38	4.92
including	219.64	220.94	1.30	12.98	0.97	13.95
MJ-07-13	463.7	467.10	3.40	3.09	0.05	3.14
including	463.7	464.55	0.85	4.92	0.03	4.95
and	465.5	465.80	0.30	4.51	0.07	4.58
and	466.55	467.10	0.55	8.90	0.18	9.08
MJ-07-15A	460.25	460.65	0.40	2.77	0.69	3.46
MJ-07-15A	462.90	463.25	0.35	3.25	0.02	3.27
MJ-07-17A	455.75	458.45	2.70	19.89	0.27	20.16
including	456.65	457.85	1.20	41.04	0.35	41.39
MJ-07-18	478.85	479.85	1.00	6.17	3.05	9.22
including	478.85	479.30	0.45	8.07	6.24	14.31
MJ-07-18	483.95	485.00	1.05	3.04	0.11	3.15
including	483.95	484.40	0.45	4.55	0.18	4.73

Merrex Gold Inc. JUBILEE PROPERTY
MJ-07-20 to MJ-07-30 Assay Summary

Hole	From (m)	To (m)	Interval (m)	Weighted Average		
				Zn %	Pb %	Pb% + Zn%
MJ-07-20	487.40	491.65	4.25	0.95	0.11	1.07
including	487.40	488.70	1.30	2.87	0.28	3.15
MJ-07-21	no significant assays					
MJ-07-22	366.75	368.70	1.95	0.79	0.14	0.92
including	366.75	367.15	0.40	2.12	0.55	2.67
MJ-07-23	no significant assays					
MJ-07-24	380.80	390.40	9.60	4.62	0.69	5.30
including	383.65	387.80	4.15	9.09	1.16	10.25
MJ-07-25	366.50	366.95	0.45	0.85	0.20	1.05
MJ-07-26	388.10	397.00	8.90	1.14	0.25	1.39
including	388.10	388.52	0.42	5.23	0.70	5.93
and	390.75	392.55	1.80	1.21	0.70	1.91
MJ-07-27	372.33	374.62	2.29	3.66	0.13	3.79
including	372.33	373.56	1.23	5.48	0.19	5.67
MJ-07-29	no significant assays					
MJ-07-30	359.50	360.30	0.80	0.97	0.68	1.65
MJ-07-30	363.10	363.30	0.20	1.42	0.06	1.47

Merrex Gold Inc. Jubilee Property

MJ-07-33 to MJ-07-55A

Hole	From (m)	To (m)	Interval (m)	Weighted Average		
				Zn %	Pb %	Zn% + Pb%
JUBILEE MAIN ZONE						
MJ-07-54	420.75	429.80	9.05	2.34	0.54	2.88
including	423.15	426.50	3.35	4.41	0.87	5.29
MJ-07-55A	406.40	408.90	2.50	0.91	0.05	0.95
including	406.40	407.10	0.70	1.65	0.07	1.72
and	408.40	408.90	0.50	2.19	0.12	2.31
ROAD ZONE						
MJ-07-33	9.00	9.40	0.40	2.48	0.01	2.49
MJ-07-34	47.25	48.00	0.75	0.59	0.07	0.66
MJ-07-35	57.70	58.70	1.00	0.93	0.20	1.13

MJ-07-35	61.55	65.65	4.10	0.75	0.64	1.39
MJ-07-36	78.60	83.00	4.40	0.80	0.02	0.82
including	78.60	79.00	0.40	2.27	0.01	2.28
and	81.30	82.00	0.70	2.31	0.01	2.32
MJ-07-38	33.00	35.00	2.00	1.69	0.93	2.62
MJ-07-38	36.00	38.40	2.40	0.95	0.17	1.12
MJ-07-39	43.30	43.80	0.50	2.34	1.35	3.69
MJ-07-39A	51.00	53.00	2.00	0.76	0.32	1.08
MJ-07-42	78.10	78.85	0.75	0.50	0.02	0.51
MJ-07-44	99.85	100.85	1.00	0.56	0.03	0.59
MJ-07-45	81.40	83.00	1.60	0.50	0.11	0.61
MJ-07-47	48.65	49.65	1.00	0.70	0.02	0.72
MJ-07-47	52.20	53.20	1.00	1.47	0.01	1.48

**Merrex Gold Inc. - Jubilee Property
Assay Results Summary: MJ-08-56 to MJ-08-72**

Drill Hole	From (metres)	To (metres)	Thickness (metres)	Weighted Average (%)		
				Zn	Pb	Zn+Pb
MJ-08-56	409.55	410.55	1.00	1.39	0.03	1.42
MJ-08-56	416.05	416.80	0.75	1.23	0.04	1.27
MJ-08-57	423.85	425.45	1.60	1.60	0.07	1.67
MJ-08-57	428.90	431.40	2.50	1.34	0.08	1.42
MJ-08-58	357.35	358.05	0.70	2.11	0.38	2.49
MJ-08-58	366.60	371.00	4.40	1.16	0.18	1.34
MJ-08-59	351.00	362.65	11.65	7.96	3.32	11.29
including	352.00	355.60	3.60	17.20	4.60	21.81
MJ-08-60A	344.75	355.05	10.30	1.79	0.61	2.40
including	344.75	348.35	3.60	2.74	0.97	3.71
MJ-08-61	342.50	343.20	0.70	8.32	0.03	8.35
MJ-08-61	348.10	348.60	0.50	2.62	0.82	3.44
MJ-08-62	348.00	349.00	1.00	3.05	0.45	3.50
MJ-08-62	352.40	360.00	7.60	1.52	0.67	2.20
including	352.40	353.40	1.00	3.02	2.11	5.13
MJ-08-63	323.00	325.00	2.00	0.99	1.28	2.27
MJ-08-64	325.70	326.70	1.00	1.83	0.13	1.96
MJ-08-65	318.80	320.60	1.80	0.88	0.52	1.40
MJ-08-66	306.65	307.15	0.50	0.34	0.13	0.47

MJ-08-67	316.70	317.50	0.80	5.02	0.33	5.35
MJ-08-67	320.45	323.40	2.95	0.92	0.18	1.11
MJ-08-68	317.60	319.40	1.80	4.78	0.11	4.89
MJ-08-69	322.05	325.95	3.90	2.48	0.06	2.54
MJ-08-70A	331.80	334.80	3.00	0.64	0.09	0.73
MJ-08-71	332.10	333.00	0.90	0.56	0.11	0.67
MJ-08-72	340.20	345.20	5.00	0.36	0.18	0.54

Merrex Gold Inc. - Jubilee Property
Assay Results Summary: MJ-10-73 to MJ-10-78

Drill Hole	From (metres)	To (metres)	Interval (metres)	Weighted Average		
				Zn %	Pb %	Pb% + Zn%
MJ-10-73	160.55	182.72	22.17	2.01	0.19	2.21
including	164.33	169.55	5.22	2.68	0.24	2.93
including	164.33	164.65	0.32	8.15	1.43	9.58
MJ-10-73	177.59	180.42	2.83	5.03	0.54	5.57
including	178.60	179.60	1.00	8.25	0.58	8.83
MJ-10-74	197.97	214.24	16.27	2.10	0.52	2.63
including	197.97	207.24	9.27	2.23	0.43	2.66
including	209.24	212.24	3.00	3.19	1.06	4.25
MJ-10-74	216.81	219.81	3.00	1.89	1.05	2.94
MJ-10-75	201.97	218.05	16.08	1.89	0.53	2.42
including	202.79	206.97	4.18	3.09	0.74	3.83
including	213.02	217.05	4.03	2.33	0.67	3.00
MJ-10-76	217.82	220.22	2.40	1.40	0.94	2.34
MJ-10-76	223.51	224.83	1.32	1.80	1.01	2.81
MJ-10-77	106.67	109.07	2.40	1.32	0.07	1.39
MJ-10-77	203.67	214.24	10.57	3.40	1.40	4.80
including	203.67	208.00	4.33	5.01	2.98	8.00
including	203.67	204.22	0.55	13.05	20.50	33.55
MJ-10-77	220.35	224.20	3.85	4.27	0.48	4.76
MJ-10-78	214.15	218.78	4.63	1.12	0.74	1.86
MJ-10-78	225.78	229.62	3.84	1.03	0.17	1.20
including	228.62	229.62	1	2.25	0.19	2.44